

PAVEMENT CONDITION INDEX SCORES

Condition	Rating Index	Definition
Good	86-100	Stable, no cracking, no patching and no deformation. Very good riding qualities.
Satisfactory	71-85	Stable, minor cracking, generally hairline and hard to detect. Minor patching and possibly some minor deformation evident. Dry or light colored appearance. Good riding qualities. Rutting less than ½".
Fair	56-70	Generally stable, minor areas of structural weakness evident. Cracking is easier to detect, patches evident. Cracking is easier to detect, patched but not excessively. Deformation more pronounced and easily noticed. Ride qualities are good to acceptable.
Poor	41-55	Areas of instability, marked evidence of structural deficiency, large crack patterns (alligating) heavy and numerous patches, deformation very noticeable. Riding qualities range from acceptable to poor.
Very Poor/Serious	11-40	Pavement in extremely deteriorated condition. Numerous areas of instability. Majority of section showing structural deficiency. Ride quality is poor.
Failed	0-10	Pavement structure failed. All of section showing severe structural deficiency.